

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08K 5/13, C08L 67/02, C08G 63/91, 63/193, C08J 5/18, B65D 1/00	A1	(11) International Publication Number: WO 99/32548 (43) International Publication Date: 1 July 1999 (01.07.99)
(21) International Application Number: PCT/US98/26424 (22) International Filing Date: 11 December 1998 (11.12.98) (30) Priority Data: 08/995,245 19 December 1997 (19.12.97) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: GOHIL, Rameschchadra, M.; 1261 Northview Porte, Circleville, OH 43113 (US). LEE, Ross, A.; 48 Hillview Avenue, Chesapeake City, MD 21915 (US). (74) Agent: GOLIAN, Andrew, G.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CN, JP, KR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: POLYESTER COMPOSITION HAVING IMPROVED GAS BARRIER PROPERTIES (57) Abstract Polyester compositions are disclosed for use in the form of a film or container having improved gas barrier properties comprising homo- or copolyesters derived from terephthalic acid or mixtures of terephthalic acid with 2,6-naphthalene dicarboxylic acid or isophthalic acid and a glycol component, such as ethylene glycol, and containing from 5 to 17 mole % of a biphenol aromatic hydroxy compound. Films of these compositions are characterized by having greatly reduced oxygen permeabilities and can be used for packaging materials, particularly, for packaging food or drink.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLEPOLYESTER COMPOSITION HAVING IMPROVED
GAS BARRIER PROPERTIESBACKGROUND OF THE INVENTION

5 This invention relates to a polyester composition, and in particular to an article, such as a film or container produced therefrom having improved gas barrier properties.


Polyester materials are particularly suitable for forming into films, containers and bottles for use as packaging materials for foodstuffs and beverages
10 such as soft drinks and beer. Unfortunately, polyester materials are permeable to some extent to gases such as carbon dioxide, and the ingress of oxygen which may affect the flavor of the packaged contents. The situation can be improved by coating the polyester film, container or bottle with a layer of barrier material which has low gas permeability, e.g., a polyvinylidene chloride copolymer.

15 However, coated materials have various disadvantages such as the need for a relatively thick coating layer, the extra costs involved with the use of additional polymers and processing steps, toxicity and delamination.

Another approach for improving gas barrier properties involves the preparation of multilayered articles, such as bottles, containing individual barrier
20 layers. However, this approach adds extra cost since additional layers must be used.

The present invention provides a polyester composition which can be made into an article such as a film, container or bottle which has improved gas barrier properties without the necessity of using additional coating materials or
25 multilayer structures.

U.S. 4,474,918 discloses improvement of gas barrier properties by melting and blending a polyester with a naphthalene diol or a bisphenol of the formula



30

where Y is $-(CH_3)_2-$, $-SO_2-$ or $-S-$. When the product is actually molded into a film, gas barrier performance is improved but there is a marked reduction in mechanical properties. In the polyester composition of the present invention, Y is a direct bond and not a divalent bridging group.

35 Japanese laid-open patent application 4(1992)-11651 discloses a polyester composition having good gas barrier properties, transparency and mechanical properties obtained by adding from 0.1 to 30 parts by weight of 1-naphthol,

2-naphthol, triphenylcarbinol, hydroquinone, resorcinol or catechol to 100 parts by weight of the polyester.

The polyester composition of the present invention differs from the aforementioned prior art polyester compositions in that it contains a specific
5 4,4'-biphenol, 2,2'-biphenol or 3,3'-biphenol aromatic hydroxy compound or mixed biphenol isomers or mixtures thereof, which provides greatly improved gas barrier properties without the loss of transparency or reduction in mechanical properties.

SUMMARY OF THE INVENTION

10 According to the present invention, there is provided a polyester composition having improved gas barrier properties comprising a dicarboxylic acid component selected from the group consisting of terephthalic acid and mixtures of terephthalic acid with up to 5 mole % of 2,5-, 2,6- or 2,7-naphthalene
15 dicarboxylic acid or isophthalic acid and an aliphatic glycol component containing from 2 to 16 carbon atoms, wherein the polyester composition contains from 1 to 17 mole %, based on the total molar amount of the polyester, of an aromatic hydroxy compound selected from the group consisting of 4,4'-biphenol, 2,2'-biphenol, 3,3'-biphenol, biphenol mixed isomers and mixtures thereof.

DETAILED DESCRIPTION OF THE INVENTION

20 The polyester component of the present invention may be a synthetic thermoplastic polyester, particularly a synthetic linear polyester, obtained by condensing terephthalic acid or its lower alkyl (up to 6 carbon atoms) diester with one or more aliphatic glycols containing from 2 to 6 carbon atoms. Mixtures of terephthalic acid or ester containing up to 5 mole % of 2,5-, 2,6- or
25 2,7-naphthalene dicarboxylic acid or isophthalic acid may also be used.

Aliphatic glycols include ethylene glycol, propylene glycol, diethylene glycol, 1,2-propylene glycol, 2,4-dimethyl-2-ethylhexane-1,3-diol, 2,2,4-trimethyl-1,3-pentanediol, 2,2-dimethyl-1,3-propanediol, 2-ethyl-2-butyl-1,3-propanediol, 2,2-diethyl-1,3-propanediol, 2-methyl-2-propyl-1,3-propanediol,
30 2-ethyl-2-isobutyl-1,3-propanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 2,2,4-trimethyl-1,6-hexanediol, 1,2-cyclohexanedimethanol, 1,4-cyclohexanedimethanol and 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Particularly preferred is ethylene glycol which when used herein may also contain diethylene glycol in amounts of from 0.5 to 2.5 mole %
35 based on the total moles of ethylene glycol present.

Polyethylene terephthalate (which term herein includes not only the homopolymer formed by poly-condensation of hydroxyethyl terephthalate but also copolymers containing up to 5 mole % of units derived from naphthalene

dicarboxylic acid or isophthalic acid and other aliphatic glycols) is particularly preferred.

The inherent viscosities (IV) of the polyesters herein are determined according to ASTM Method D2857 using a Cannon Ubbelohde viscometer using
5 a polymer concentration of 0.5% by weight in 25/75 by volume trifluoroacetic acid/methylene chloride at $30 \pm 0.1^\circ\text{C}$. The IV of the polyester composition of the invention can range from 0.50 to 0.60 dl/g or higher. If the IV is less than 0.50, an undesirable reduction in mechanical properties may occur.

According to the present invention, gas barrier properties of a polyethylene
10 terephthalate composition surprisingly can be greatly improved by incorporating from 1 to 17 mole %, preferably from 5 to 12 mole %, based on the total molar amount of the polyester, of an aromatic hydroxy compound selected from 4,4'-biphenol, 2,2'-biphenol, 3,3'-biphenol, mixed biphenol position isomers including 2,3'-biphenol, 3,4'-biphenol and 2,4'-biphenol resulting from the
15 oxidative coupling of phenol and mixtures thereof. A biaxially stretched, heat-set film formed from the polyester composition has an oxygen permeability of less than 3.0 cc-mil/100 in²-24 hours-atm. The PET composition also exhibits excellent transparency and mechanical properties.

If the content of the aromatic hydroxy compound is less than 1 mole %,
20 the improvement in the gas barrier properties of the polyethylene terephthalate composition may be insufficient for some applications. On the other hand, if the content of the aromatic hydroxy compound exceeds 17 mole % the polymer melting point and crystalline character decrease dramatically, thereby adversely affecting the transparency and mechanical properties.

25 In another embodiment of the invention, the gas barrier properties of a polyethylene terephthalate composition can be improved by using 4,4'-biphenol, 2,2'-biphenol, 3,3'-biphenol, biphenol mixed isomers or mixtures thereof in the form of an oligoester comprising the biphenol compound, the dicarboxylic acid component and the glycol component having a number average molecular weight
30 of less than 4000.

The dramatic improvement in gas barrier properties obtained in the present invention is believed partly due to the presence of biphenol units introduced into the PET which can provide unique crystallization sites as well as chain stiffening segments and reduce free volume, thereby uniquely hindering the diffusion of gas
35 while improving mechanical properties. In addition, high gas barrier can arise from the reduction in localized motion along the molecular backbone, i.e., hindrance to micro Brownian motion, due to interaction of phenolic chain ends on the polymer molecules and free biphenol with polyester molecules.

The polyester compositions are prepared by blending the aromatic hydroxy compound with the PET, and melting and kneading the blend in an extruder to form mixed chips or pellets. Copolyester compositions of the invention may also be formed by direct polymerization of the aromatic hydroxy compound and PET monomer components.

If desired, conventional additives such as dyes, pigments, stabilizers, plasticizers, fillers, ultraviolet absorbers, fluorescent brighteners, antistatic agents, mold release agents, and the like, may be added to the polyester composition in typical amounts.

The polyester composition of the present invention can be formed into an article such as a film, container, bottle or any similar receptacle that can be used for packaging materials, and particularly for packaging food and drink.

As regards to films, a polyethylene terephthalate film is particularly preferred, especially a film which has been biaxially oriented by sequential stretching or simultaneous stretching in two mutually perpendicular directions, typically at a temperature in the range of 70° to 125°C, preferably from 75° to 95°C, and preferably heat set, typically at a temperature in the range of 150° to 250°C, preferably from 180° to 220°C.

A polyester film prepared from a polyester composition of the invention may be unoriented, or uniaxially oriented, but is preferably biaxially oriented by stretching sequentially or simultaneously in two mutually perpendicular directions in the plane of the film to achieve a satisfactory combination of mechanical and physical properties. Stretching may be effected in a tenter frame by extruding the polyester as a flat extrudate that is subsequently stretched first in one direction and then in the other mutually perpendicular direction or simultaneously in both directions. Generally, it is preferred to stretch first in the longitudinal direction, and then in the transverse direction. The stretched polyester film may be, and preferably is, dimensionally stabilized by heat-setting under dimensional restraint at a temperature above the glass transition temperature thereof.

Polyester compositions of the present invention can also be fabricated into containers, such as bottles, by an injection or blow molding process wherein a preform is heated and stretched both axially and radially so as to confer biaxial orientation. The polyester hollow molded product has a high mechanical strength as well as excellent transparency and gas barrier properties, and can be widely used for fresh beverage, flavoring material, oil, alcoholic drink such as beer and wine and cosmetics. Particularly, the hollow polyester molded product can be used as a small-sized container for carbonated drink, beer, wine, or the like, which

would not be preserved for a predetermined guaranteed period due to the insufficient gas barrier property using a conventional biaxially stretched polyethylene terephthalate bottle.

5 The invention will be further illustrated by the following examples although it is understood that these examples are included merely for purposes of understanding and are not intended to limit the scope of the invention.

10 In the following examples, oxygen permeability is calculated in cubic centimeters of O₂ permeating a 1-mil thick sample, per 100 inches square, over a 24-hour period under an O₂ partial pressure difference of one atmosphere at 30°C using a Mocon OX-TRAN twin instrument and is reported as cc-mil/100 in²-24 hours-atm.

EXAMPLES 1 TO 6

(COMPARATIVE EXAMPLES 1C TO 5C)

15 Polyethylene terephthalate (PET) having an IV of 0.85 dl/g was melt blended with the aromatic hydroxy compounds shown in Table I in a twin screw extruder at a temperature range of 250° to 265°C to form pellets which were dried at 120°C. Amorphous cast films having a thickness of from 5 to 10 mils were made from the dried pellets in a press heated at 270°C. The films were simultaneously stretched in the temperature range of 80° to 95°C at a stretch ratio
20 of 3.5 X 3.5 (MD/TD) and strain rate of 9000% per minute. The films were subsequently heat-set at 180°C. Oxygen permeability values are shown in Table I. From the results, it can be seen that more than a 50% reduction in oxygen permeability (2X the barrier) was obtained for PET made by adding either 11 mole % of 4,4'-biphenol or 10 mole % of a combination of 5 mole %
25 4,4'-biphenol and 5 mole % of naphthalene dicarboxylic acid.

Table I

Example No.	Polyester Composition (mole %)	Stretch Ratio (MDXTD)	T _s (°C)	HST (°C)	Oxygen* Permeability	MP (°C)	IV (dl/g)
-	PET	3.5 X 3.5	85	180	6.5	255	0.85
-	PET	3.5 X 3.5	95	NHS	8.0	255	0.85
-	PET	Cast	-	-	9.9	255	0.59
1	PET-5% BP	3.5 X 3.5	80	180	3.0	250	0.52
2	PET-5% BP	3.5 X 3.5	90	180	3.0	250	0.52
3	PET-11% BP	3.5 X 3.5	85	180	2.3	245	0.55
4	PET-11% BP	3.5 X 3.5	85	NHS	2.0	245	0.55
5	PET-5% BP-5% NDCA	3.5 X 3.5	95	180	2.8	243	0.60
6	PET-5% BP-5% NDCA	3.5 X 3.5	85	180	2.7	243	0.60
1C	PET-5% BISP-A	3.5 X 3.5	90	NHS	4.3	249	0.53
2C	PET-5% BISP-A-5% NDCA	3.5 X 3.5	95	180	4.6	249	0.54
3C	PET-5% BISP-A-5% NDCA	3.5 X 3.5	80	NHS	5.1	249	0.54
4C	PET-5% BISP-A-5% NDCA	3.5 X 3.5	80	180	3.64	249	0.54
5C	PET-6% NDCA	3.5 X 3.5	95	180	4.1	-	0.60

BP = 4,4'-biphenol; BISP-A = bisphenol-A;

NDCA = naphthalene dicarboxylic acid

T_s = Stretch temperature; IV = intrinsic viscosity

NHS = not heat-set

HST = heat-setting temperature; MP = melting point

* cc-mil/100 in²-24 hours-atm

EXAMPLES 7 TO 9
(COMPARATIVE EXAMPLE 6C)

Amorphous cast films of polyethylene terephthalate (PET) containing 3 mole % of isophthalic acid and 4,4'-biphenol were prepared as described in Examples 1 to 6. The films were stretched at a stretch ratio of 3.5 X 3.5 (MD/TD) at a stretching temperature of 85°C with strain rate of 9000% per minute. Non heat-set films were used for oxygen permeability measurements.

The results in Table II illustrate the large reduction in oxygen permeability that can be obtained using the polyester composition of the invention.

The total amount (mole %) of BP contained in the polyester film composition was determined by ¹H-NMR. From 4 to 7 mole % of BP provided optimum oxygen barrier properties of 50 to 66% without affecting transparency or mechanical properties.

TABLE II

Example No.	Polyester Composition (mole %)	Stretch Ratio (MDXTD)	Ts (°C)	HST (°C)	Oxygen* Permeability	MP (°C)	IV (dl/g)	% BP (by NMR)
7	PET-8% BP-3% ISP	3.5 X 3.5	85	-	2.1	241	0.50	6.5
8	PET-10% BP-3% ISP	3.5 X 3.5	85	-	2.0	238	0.49	7.0
9	PET-5% BP-3% ISP	3.5 X 3.5	85	-	2.8	244	0.57	4.2
6C	PET-3% ISP	3.5 X 3.5	85	-	5.9	246	0.72	-

ISP = isophthalate

* cc-mil/100 in²-24 hours-atm

What is claimed is:

1. A polyester composition having improved gas barrier properties comprising a dicarboxylic acid component selected from the group consisting of terephthalic acid and mixtures of terephthalic acid with up to 5 mole % of 2,5-,
5 2,6- or 2,7-naphthalene dicarboxylic acid or isophthalic acid and an aliphatic glycol component containing from 2 to 16 carbon atoms, wherein the polyester composition contains from 1 to 17 mole %, based on the total molar amount of the polyester, of an aromatic hydroxy compound selected from the group consisting of 4,4'-biphenol, 2,2'-biphenol, 3,3'-biphenol, biphenol mixed isomers and mixtures
10 thereof.
2. The polyester composition of Claim 1 wherein the glycol component comprises ethylene glycol and the aromatic hydroxy compound comprises 4,4'-biphenol.
3. The polyester composition of Claim 2 wherein the dicarboxylic acid
15 component comprises terephthalic acid.
4. The polyester composition of Claim 2 wherein the dicarboxylic acid component comprises a mixture of terephthalic acid and up to 5 mole % of 2,6-naphthalene dicarboxylic acid.
5. The polyester composition of Claim 2 wherein the dicarboxylic acid
20 component comprises a mixture of terephthalic acid and up to 5 mole % of isophthalic acid.
6. The polyester composition of Claim 1 wherein the biphenol mixed isomers include 2,3'-biphenol, 3,4'-biphenol and 2,4'-biphenol resulting from the oxidative coupling of phenol.
- 25 7. The polyester composition of Claim 1 wherein the polyester comprises polyethylene terephthalate.
8. An article formed from the polyester composition of Claim 1.
9. The article of Claim 8 in the form of a film having an oxygen permeability of less than 3.0 cc-mil/100 in²-24 hours-atm.
- 30 10. The film of Claim 9 which is biaxially oriented.
11. The article of Claim 8 in the form of a bottle.
12. The bottle of Claim 11 which is biaxially oriented and formed from a preform which is stretched axially and radially.
13. The polyester composition of Claim 1 comprising an oligoester of the
35 4,4'-biphenol, 2,2'-biphenol, 3,3'-biphenol, biphenol mixed isomers or mixtures thereof, the dicarboxylic acid component and the aliphatic glycol component, the oligoester having a number average molecular weight of less than 4000.
14. The polyester composition of Claim 13 wherein the oligoester comprises terephthalic acid, ethylene glycol and 4,4'-biphenol.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/26424

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08K5/13 C08L67/02 C08G63/91 C08G63/193 C08J5/18
B65D1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K C08L C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 342 902 A (DARNELL, W. RONALD ET AL) 30 August 1994 see claim 24; example 19; table III see column 4, line 33 - line 39 ---	1-3,7,8, 11
X	Y. SAKAGUCHI ET AL.: MACROMOLECULES, vol. 28, no. 18, 1995, pages 6155-6160, XP002100454 see page 6155 - page 6156 ---	1-3,7
X	CHEMICAL ABSTRACTS, vol. 94, no. 4, 26 January 1981 Columbus, Ohio, US; abstract no. 16390, XP002100455 see abstract & JP 55 106222 A (TORAY IND.) 14 August 1980 --- -/-	1-3,7-10



Further documents are listed in the continuation of box C



Patent family members are listed in annex

Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

20 April 1999

Date of mailing of the international search report

06/05/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Krische, D

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/26424

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 2 718 139 A (DAINIPPON INK & CHEMICALS) 6 October 1995 see abstract see application experiments 1,2 ---	1-3,7,8
X	DATABASE WPI Section Ch, Week 9338 Derwent Publications Ltd., London, GB; Class A23, AN 93-299696 XP002100457 & JP 05 214085 A (TOYOCO KK) , 24 August 1993 see abstract ---	1-3,7
A	US 4 474 918 A (SEYMOUR, ROBERT W. ET AL) 2 October 1984 cited in the application see the whole document ---	1-3,7-9
A	US 5 641 548 A (YAMAMOTO, KAZUHITO ET AL) 24 June 1997 see claim 1; examples 1,5,25 ---	1-5,8, 11,12
A	EP 0 379 824 A (EASTMAN KODAK CO) 1 August 1990 see abstract; claim 1; example 4 see page 3, line 36 - line 45 ---	1,7-10
A	CHEMICAL ABSTRACTS, vol. 115, no. 14, 7 October 1991 Columbus, Ohio, US; abstract no. 137814, XP002100456 see abstract & JP 03 071842 A (TORAY IND.) 27 March 1991 -----	1,8-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/26424

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5342902	A	30-08-1994	NONE	
FR 2718139	A	06-10-1995	DE 4411361 C	16-11-1995
			CA 2145457 A	01-10-1995
			GB 2289051 A,B	08-11-1995
			JP 7304860 A	21-11-1995
			US 5488093 A	30-01-1996
US 4474918	A	02-10-1984	NONE	
US 5641548	A	24-06-1997	JP 2741916 B	22-04-1998
			JP 3087232 A	12-04-1991
			JP 2740288 B	15-04-1998
			JP 3087229 A	12-04-1991
			JP 2741914 B	22-04-1998
			JP 3087230 A	12-04-1991
			JP 2741915 B	22-04-1998
			JP 3087231 A	12-04-1991
			JP 2741918 B	22-04-1998
			JP 3087234 A	12-04-1991
			JP 2741919 B	22-04-1998
			JP 3087235 A	12-04-1991
			JP 2741920 B	22-04-1998
			JP 3087236 A	12-04-1991
			JP 2741921 B	22-04-1998
			JP 3087237 A	12-04-1991
			US 5571584 A	05-11-1996
			US 5556675 A	17-09-1996
			AT 147321 T	15-01-1997
			CA 2024330 A,C	01-03-1991
			DE 69029623 D	20-02-1997
			DE 69029623 T	26-06-1997
			EP 0415728 A	06-03-1991
			HK 1000063 A	07-11-1997
			KR 9406645 B	25-07-1994
			JP 2872358 B	17-03-1999
			JP 3162926 A	12-07-1991
EP 0379824	A	01-08-1990	CA 2005646 A	23-06-1990
			WO 9007553 A	12-07-1990

100

100

100